

Metamark Frost, Crystal, Dusted and Silver Etch

Etch Glass Effect Films



Light Transmission, Solar Energy & UV Performance Table

The following provides a guide to the light transmission, solar energy and UV performance parameters of the Metamark Etch Glass films.

	M4-OF Metamark Frost	M7-CR Metamark Crystal Etch	M7-DE Metamark Dusted Etch	M7-SE Metamark Silver Etch
Solar Energy Transmission, %	87%	60%	87%	74%
Solar Energy Reflection, %	8%	26%	8%	19%
Solar Energy Absorption, total, %	4%	14%	5%	7%
Visible Light Transmission, %	90%	61%	90%	75%
Visible Light Reflection, adhesive side, %	8%	27%	8%	20%
Visible Light Reflection, film side, %	8%	26%	8%	20%
UV Transmission, %	> 5%	> 5%	> 5%	> 5%
g value	0.88	0.63	0.88	0.75
Total Solar Energy Rejected, %	12%	37%	12%	25%
Glare Reduction, total	10	30	8	14

The data are given for the adhesive side facing towards the sun. This information is given 'as is'; and given in good faith as correct. No warranty can be given regarding its reliability.

Warranty: Metamark (UK) Limited warrants to its customers that completed decorative markings which utilise Metamark SignVinyl will remain in good condition without excessive fading or colour degradation for the specified life time of each material when correctly stored and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark SignVinyl becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will also, at its own discretion, contribute an allowance towards the costs involved in replacing the graphics. **Please Note:** The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

Metamark (UK) Limited

○ Luneside · New Quay Road · Lancaster · LA1 5QP · Tel +44 (0)1524 387140 · Fax +44 (0)1524 387147
○ Octimum Business Park · Forsyth Road · Woking · GU21 5 SF · Tel +44 (0)1483 571111 · Fax +44 (0)1483 570540

Email sales@metamark.co.uk
www.metamark.co.uk